

PRIMARY ALUMINIUM

- Primary aluminium A8, A7, A7E

Application: widely used industry. Power lines, food and catering equipment, packaging for the food industry, food wrap, additionally chemical, electrical and electronic equipment are produced from this metal.

Packing : ingots 12-26kg placed on a pallet app. 1 T or "T-bars" weighing approximately 0,750 T.

Grade acc. GOST 11069- 2001	Chemical composition, %									
	Al %	Other max %								
	min.	Si	Fe	Cu	Mn	Mg	Zn	Ga	Ti	Other
A8	99,8	0,1	0,12	0,01	0,02	0,02	0,04	0,03	0,01	0,02
A7	99,7	0,15	0,16	0,01	0,03	0,02	0,04	0,03	0,01	0,02
A7E	99,7	0,08	0,2	0,01	*	0,02	0,04	0,03	0,01 **	0,02

** Sum of Ti, V, Cr, Mn